



REPLACEMENT CLAIM SET (WITH CHANGES NOTED)

- 1) (PREVIOUSLY AMENDED) A method for deinking waste paper comprising the steps of:
 - a) converting the waste paper to a pulp slurry having a pH of from about 6.0 to about 8.8;
 - b) contacting the pulp slurry with a deinking blend comprising a first alkoxyated fatty alcohol having a HLB of at least 13 and a first fatty acid, wherein said deinking blend comprises from about 20 wt.% to about 60 wt.% of said first fatty acid; and
 - c) separating ink from the pulp slurry by flotation.
- 2) (ORIGINAL) The method of claim 1, wherein the first fatty acid is non-alkoxyated.
- 3) (ORIGINAL) The method of claim 1, wherein the first fatty acid is more than 20 wt% fatty acid having at least 16 carbon atoms and less than 60 wt% of saturated fatty acid having 14 carbons or less.
- 4) (ORIGINAL) The method as in claim 1, wherein the first fatty acid comprises 6 to 20 carbon atoms.
- 5) (ORIGINAL) The method of claim 1, wherein, in step b), the deinking blend further comprises a second alkoxyated fatty alcohol.
- 6) (ORIGINAL) The method of claim 5, wherein the second alkoxyated fatty alcohol is of the formula:




- a) wherein:
 - b) R is a straight or branched alkyl group;
 - c) n is from about 10 to about 100;
 - d) m is from about 1 to about 35; and
 - e) said n $\text{-(CH}_2\text{-CH}_2\text{-O)-}$ units and said m $\text{-(CH}_2\text{-CH(CH}_3\text{)-O)-}$ units are ordered in block or random format in any order or sequence.
- 7) (ORIGINAL) The method of claim 1, wherein the first alkoxyated fatty alcohol is of the formula:



- a) wherein:

- b) R is a straight or branched alkyl group;
 - c) n is from about 5 to about 40;
 - d) m is from about 0 to about 20; and
 - e) said n $-(\text{CH}_2-\text{CH}_2-\text{O})-$ units and said m $-(\text{CH}_2-\text{CH}(\text{CH}_3)-\text{O})-$ units are ordered in block or random format in any order or sequence.
- 8) (ORIGINAL) The method of claim 7, wherein R is a C₆ to C₂₀ alkyl.
 - 9) (ORIGINAL) The method of claim 1, further comprising adding sodium silicate or sodium sulfite or a combination thereof to the pulp slurry.
 - 10) (CANCELED)
 - 11) (ORIGINAL) The method of claim 1, further comprising adding a flotation additive to the slurry before or during separating ink from the pulp slurry.
 - 12) (PREVIOUSLY AMENDED) The method of claim 1, further comprising adding one cationic additive to the slurry before or during the flotation.
 - 13) (ORIGINAL) The method of claim 12, wherein the cationic additive is a cationic polymer.
 - 14) (ORIGINAL) The method of claim 13, wherein the cationic additive is a cationic polyamine.
 - 15) (ORIGINAL) The method of claim 1, wherein the first alkoxyated fatty alcohol comprises at least 5 moles of ethoxylation.
 - 16) (ORIGINAL) The method of claim 1, wherein the alcohol portion of the first alkoxyated fatty alcohol comprises 6 to 20 carbon atoms.
 - 17) (CANCELLED)
 - 18) (ORIGINAL) The method of claim 1, wherein the pulp slurry in step a) has a pH of from about 6.8 to about 7.2.
 - 19) (ORIGINAL) The method of claim 1, wherein the blend is a liquid at a temperature of at least 22 °C.
 - 20) (CANCELED)
 - 21) (CANCELED)
 - 22) (ORIGINAL) The method of claim 1, wherein the first alkoxyated fatty alcohol and first fatty acid are present in a ratio of from about 1:2 to about 2:1 by weight.

- 23) (CANCELED)
- 24) (CANCELED)
- 25) (ORIGINAL) The method of claim 5, wherein the blend comprises alkoxyated fatty alcohol and fatty acid in a ratio of from about 1:2 to about 3:1 by weight.
- 26) (ORIGINAL) The method of claim 1, wherein the blend comprises water or other diluent.
- 27) (ORIGINAL) The method of claim 1, wherein the blend comprises from about 0 to about 25 weight % water or other diluent.
- 28) (ORIGINAL) The method of claim 1, wherein the first fatty acid is a tall oil fatty acid.
- 29) (ORIGINAL) The method of claim 1, wherein the blend further comprises a second fatty acid, wherein the second fatty acid is an alkoxyated fatty acid of the formula:




wherein:

- a) R^2 is a straight or branched alkyl group comprising at least 6 carbon atoms;
- b) p is from about 10 to about 100;
- c) q is from about 0 to about 50; and
- d) said p $-(CH_2-CH_2-O)-$ units and said q $-(CH_2-CH(CH_3)-O)-$ units are ordered in block or random format in any order or sequence.
- 30) (ORIGINAL) The method of claim 29, wherein R^2 is a C6 to C20 alkyl.
- 31) - 59) (CANCELED)
- 60) (PREVIOUSLY AMENDED) A method for deinking waste paper comprising the steps of:
- a) converting the waste paper to a pulp slurry having a pH of from about 6.0 to about 8.8;
- b) contacting the pulp slurry with a deinking blend comprising a first alkoxyated fatty alcohol having a HLB of at least 13 and a first fatty acid, wherein said deinking blend comprises from about 20 wt.% to about 60 wt.% of said first fatty acid; and
- c) separating ink from the pulp slurry by flotation;

wherein the first alkoxyated fatty alcohol comprises at least five moles of ethoxylation;
and


wherein the first fatty acid is a non-alkoxyated C6 to C20 fatty acid.

- 61) (ORIGINAL) The method of claim 60, wherein the blend comprises a second fatty acid wherein the second fatty acid is an alkoxyated fatty acid.
- 62) (ORIGINAL) The method of claim 60, wherein the first alkoxyated fatty alcohol is of the formula:




- a) wherein:
- b) R is a straight or branched alkyl group;
- c) n is from about 5 to about 40;
- d) m is from about 0 to about 20; and
- e) said n $-(CH_2-CH_2-O)-$ units and said m $-(CH_2-CH(CH_3)-O)-$ units are ordered in block or random format in any order or sequence.
- 63) (ORIGINAL) The method of claim 62, wherein n is 12 to 25 and m is 0.
- 64) (ORIGINAL) The method of claim 62, wherein the first fatty acid is more than 20 wt% fatty acids having at least 16 carbon atoms and less than 60 wt% of saturated fatty acid having 14 carbons or less.
- 65) - 69) (CANCELLED)
- 70) (PREVIOUSLY AMENDED) A deinking composition comprising:
- a) a first fatty acid that is not alkoxyated and that comprises more than 20 wt% fatty acids having at least 16 carbon atoms and less than 60 wt% of saturated fatty acids having 14 carbons or less, wherein said deinking blend comprises from about 20 wt.% to about 60 wt.% of said first fatty acid;
- b) a first alkoxyated fatty alcohol having a HLB of at least 13;
- c) optionally a second fatty acid that is alkoxyated; and
- d) optionally a second alkoxyated fatty alcohol.
- 71) (ORIGINAL) The composition of claim 70, wherein the first fatty acid comprises from about 20 wt % to about 90 wt % of first fatty acid having at least 16 carbon atoms.

- 72) (ORIGINAL) The composition of claim 70, wherein the first fatty acid with at least 16 carbon atoms are from about 40 wt % to about 90 wt % unsaturated.
- 73) (CANCELED)
- 74) (ORIGINAL) The composition of claim 70, wherein the first alkoxyated fatty alcohol is of the formula:




wherein:

- a) R is a straight or branched alkyl group;
 - b) n is from about 5 to about 40;
 - c) m is from about 0 to about 20; and
 - d) said n $-(CH_2-CH_2-O)-$ units and said m $-(CH_2-CH(CH_3)-O)-$ units are ordered in block or random format in any order or sequence.
- 75) (ORIGINAL) The composition of claim 74, wherein n is 10 to 30 and m is less than 10.
- 76) (ORIGINAL) The composition of claim 74, wherein n is 12 to 25 and m is 0.
- 77) (ORIGINAL) The composition of claim 70, wherein the composition is a liquid at a temperature of at least 22 °C.
- 78) (ORIGINAL) The composition of claim 70, wherein the composition comprises an alkoxyated fatty acid, and said alkoxyated fatty acid is of the formula



wherein:

- a) R^2 is a straight or branched alkyl group comprising at least 6 carbon atoms;
 - b) p is from about 10 to about 100;
 - c) q is from about 0 to about 50; and
 - d) said p $-(CH_2-CH_2-O)-$ units and said q $-(CH_2-CH(CH_3)-O)-$ units are ordered in block or random format in any order or sequence.
- 79) (ORIGINAL) The composition of claim 70, further comprising a second alkoxyated fatty alcohol.
- 80) (ORIGINAL) The composition of claim 79, wherein the second alkoxyated fatty alcohol is of the formula:



- a) wherein:
- b) R is a straight or branched alkyl group;
- c) n is from about 10 to about 100;
- d) m is from about 1 to about 35; and
- e) said n $-(\text{CH}_2-\text{CH}_2-\text{O})-$ units and said m $-(\text{CH}_2-\text{CH}(\text{CH}_3)-\text{O})-$ units are ordered in block or random format in any order or sequence.